

SK world

Alenar - Article Passport

Product Features

Applications	Upholstery and Drapery
Composition faceside	100% Polyester
Statistic Code	55121990
Dyeing method	Piece dyed
Available colours	22
Minimum workable width	140 CM
Roll length	35 - 40 M
GSM	400GS/M
Backing/Finishing	Water repellent

Colours



Durability specifications

Test	Test Specification	Unit	Test result	
			WARP	WEFT
Colour Fastness To Rubbing	ISO 105-D01	Grade	4-5	4
Colour Fastness To Light	UNE 40187 / BS 1006-B02	Grade	4	
Pilling	EN ISO/DIS 12945-1	Grade	4-5	
Abrasion Resistance	EN ISO 12947-2:1998	Martindale	>40.000 Cycles	

Processing specifications

Test	Test Specification	Unit	Test result	
			WARP	WEFT
Breaking Strength	ISO 13937-3	Newton	620	390
Tearing Strength	BS 3320:1998 y BS 2543:1995	Newton	63	63

Cleaning specifications and Instructions

Test	Test Specification	Unit	Test result	
			WARP	WEFT

Instructions



Wash at or below 30°



Do not bleach



Dry clean, any solvent except trichloroethylene



Iron, low temp.



Do not tumble dry



SK world

Poligono Industrial C, Parcela B, Nave 9
Prolongación C/Braçal del Roncador
46800-Xàtiva-Valencia
España
+34 96 228 40 17