

Dakar - Article Passport

Product Features

| | |
|------------------------|-------------------|
| Product group | No Woven Back W,P |
| Applications | Upholstery |
| Composition faceside | 100% Polyester |
| Statistic Code | 55121990 |
| Dyeing method | - |
| Available colours | 25 |
| Minimum workable width | 142 CM |
| Roll length | 40 M |
| GSM | 300 GSM +/-5% |
| Backing/Finishing | Water Proof |

Colours



Durability specifications

| Test | Test Specification | Unit | Test result | |
|----------------------------|---------------------|------------|---------------|------|
| | | | WARP | WEFT |
| Colour Fastness To Rubbing | ISO 105-X12 | Grade | 4-5 | |
| Colour Fastness To Light | ISO 105-B02 | Grade | 4 | |
| Pilling | EN ISO/DIS 12945-2 | Grade | 4-5 | |
| Abrasion Resistance | EN ISO 12947-2:2016 | Martindale | 45.000 Cycles | |

Processing specifications

| Test | Test Specification | Unit | Test result | |
|-------------------|-----------------------------|------|-------------|------|
| | | | WARP | WEFT |
| TEAR STRENGTH | ISO 13937-1:2000/COR 1:2004 | mm | 63 | 63 |
| BREAKING STRENGTH | ISO 13934-2:2014 | N | 1100 | 880 |

Cleaning specifications and Instructions

| Test | Test Specification | Unit | Test result | |
|----------------------------------|---|------|-------------|-------|
| | | | WARP | WEFT |
| Dimensional Stability To Washing | ISO 3759-2011/ISO 5077-2007/ISO 6330-2012 | % | -2.1% | -1.4% |

Instructions



Wash at or below 30°



Do not bleach



Iron, low temp.



Do not dry clean



Do not tumble dry



SK world

Polígono Industrial C, Parcela B, Nave 9
 Prolongación C/Braçal del Roncador
 46800-Xàtiva-Valencia
 España
 +34 96 228 40 17