

## Enola - Article Passport

### Product characteristics

Applications	Drappery
Composition faceside	100% Polyester
Statistic Code	5512199000
Dyeing method	Piece dyed
Available colours	6
Minimum workable width	280 CM
Roll length	30 - 40 M
GSM	350GS/M

### Colors



### Dimensional Stability To Washing

(ISO 3759:2011/ISO 5077:2007/ISO 6330:2021; Using horizontal axis, front-loading type machine; Procedure No.3N, Machine Wash At 30°C; with 2.0±0.2kg total dry mass (Type III (100% Polyester) Ballast+ Specimen) and 20±1 g ECE reference detergent 98 without optical brightener, Drip Dry)

#### After 1 Wash

	Unit	A	Requirement
Lengthwise	%	-1.2	-
Widthwise	%	-1.5	-

Remark: (+) Means Growth; (-) Means Shrinkage

### Colour Fastness To Light

(ISO 105-B02:2014; Method 2 (Modified), use Xenon arc lamp, Exposure Cycle: A1, no flip-flop mode was used)

Comparison up to blue wool reference 4

	Unit	A	Requirement
Grade (B.W.S)	-	4	-

### Cleaning specifications and Instructions

Test	Test Specification	Unit	Test result	
			WARP	WEFT
Instructions				

#### Instructions



Wash at or below 30°



Do not bleach



Drip dry



Do not dryclean



Iron, low temp.



Do not tumble dry

